

# C/D PLYWOOD

In CMPC we are committed to provide high quality products and offer an excellent service. That is why we have been developing SELEX PLYWOOD; a stable and reliable Plywood panel with high quality and amazing appearance.

- Consistent top quality.
- Easy to work with
- 100% Radiata pine.
- FSC® certified product





Partition walls, flooring, ceilings and sheathing.



Partition walls, Interior sheathing for walls and celings.



Packaging and transportation.

# PRODUCT BENEFITS AND APPLICATIONS

Board intended for structural use in the construction area.

Easy handling due to their low weight - volume ratio.

It's high physical-mechanical bending, shear and compressive strength coupled with a production based on phenol-formaldehyde low emissivity (E1) resin, favor its use indoors and outdoors controlled with a high thermal insulation.

## **FEATURES**

		The same of the same of	
			6 0
		Selex C	Selex D
	Finishing		
	Sanding grade	150	120
Ī	Natural defects		
		Un to 40 man wide	He to 75 mass wilds
	Sound knots	Up to 40 mm. wide	Up to 65 mm. wide
	Unsound knots	Up to 40 mm. wide	Up to 65 mm. wide
	Knot holes	Up to 25 mm. wide	Up to 65 mm. wide
	Pitch pockets	Allowed	Allowed
	Bark pockets	Allowed	Allowed
	Freckles	Allowed	Allowed
	Machining defects		
	Open cracks	Up to 25 mm. wide	Up to 25 mm. wide
	Fungal stains	Allowed	Allowed
	Roughness	Allowed	Allowed
ì	Repairs		
	· ·	NI-t	Niekersellesleie
	Inner splits in knots	Not applicable	Not applicable
	Routings with polyurethane	Not applicable	Not applicable
	Putty patches	Not applicable	Not applicable

# **GENERAL SPECIFICATIONS**

	Thickness (mm)	6.5	9	12	15	18	21	25	
Dimensions: 4' x 8' (1,22 x 2,44 m)	THICKIESS (IIIII)	0,5	7	12	13	10	21	23	
	N° of plies	3	3	5	5	6/7	7	9	
Density	480-550 kg/m <sup>3</sup>								
Adhesive	Formaldehyde emission meet E1 standard .								
Moisture Content	8% to 12 % for all boards .								
Forestry Certification	FSC® Certified product.								