



# B/C

## PLYWOOD

At CMPC we are committed to provide high quality products and offer an excellent service. That is why we have been developing SELEX PLYWOOD; a stable and reliable Plywood panel with high quality and amazing appearance.

- High visual appearance
- Special for decorative uses
- Consistent quality
- Easy to work with



\* Ask about our FSC® certified products.

Now registered in The Dutch Environmental database



Distributed by





Decoration and furniture.







Interior and exterior decorative sheathing for walls and ceilings.





Packaging, furniture and lamination.

## PRODUCT BENEFITS AND APPLICATIONS

-  A multipurpose attractive quality panel.
-  Suitable for structural applications such as roofing, flooring and wall sheathing.
-  Easy to handle due to its excellent strength to weight ratio.
-  Outstanding visual face without open defects.

## FEATURES

		
	Selex B	Selex C
Finishing		
Sanding grade	150	150
Natural defects		
Sound knots	Up to 25 mm. wide	Up to 40 mm. wide
Unsound knots	Repaired, up to 25 mm. wide	Up to 40 mm. wide
Knot holes	Not allowed	Up to 25 mm. wide
Pitch pockets	Up to 25 mm. wide	Allowed
Bark pockets	Not allowed	Allowed
Freckles	Allowed	Allowed
Machining defects		
Open splits	Up to 1 mm. wide	Up to 25 mm. wide
Open cracks	Up to 1 mm. wide	Up to 25 mm. wide
Fungal stains	Allowed	Allowed
Roughness	Allowed	Allowed
Repairs		
Inner splits in knots	Allowed	Unrepaired, up to 1 mm. wide
Routings with polyurethane	Occasionally	Not applicable
Putty patches	Allowed	Not applicable
Single wooden patches	Allowed	Not applicable
Double wooden patches	Allowed	Not applicable
Triple wooden patches	Allowed	Not applicable

## GENERAL SPECIFICATIONS

Dimensions: 8' x 4' (2,440 x 1,220 m)	Thickness (mm)	6,5	9	12*	15*	18*	21	25
	Nº of plies	3	3	5	5	7	7	9
Density		480 – 550 kg / m³						
Adhesive		EN 636-2, EN 314-2 Class 2, CARB2 and E1 compliant.						
Structural Certification		EN 13986, CE2+ (structural).						
Moisture Content		8% to 12 % for all boards.						
Forestry Certification		FSC® certified product.						

\*Registered in The Dutch Environmental database